

X-RAY TRANSMISSION

Aluminium-equivalent measurements were carried out with 100 kV X-rays on various ROHACELL specimens. The graph shows curves measured for ROHACELL grades 31, 51 and 71. Only the given readings for the indicated thicknesses were measured for ROHACELL 110.

ROHACELL	THICKNESS in. (cm)	AL-EQUIVALENT in. (cm)
110	1.9 (48)	0.17 (0.44)

